



brilen

High tenacity polyester yarns




DEEP SEA TREATMENT

brilen.com

2024, BRILEN.

The data contained in this manual are for general information purposes only. While they reflect the state of knowledge at the time of issue, BRILEN does not give any guarantee in respect there of and accepts no liability for deviations exhibited by their products.

DEEP SEA TREATMENT



DST - LOW YARN TO YARN ABRASION

Type	Titer	Version	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA (%)
DST	2200/192	HT20	82	12,5	4,6	9
	3300/384	HT20	82	12,5	4,6	9
	6600/768	HT20	82	13,0	5,0	9

All DST type portfolio is certified according to DNV, ABS and BV and could be fulfilling other required standards.

Special constructions are available in collaboration with the most reliable converters, which are also approved by the mentioned certifiers.



Any special request on properties, spool format or certification could be available under request. Please, contact our commercial team.