



**BRILEN POLYESTER INDUSTRIAL YARNS**

P.I. Valle del Cinca s/n  
22300 Barbastro (Huesca) Spain  
Ph.: +34 974 316 065  
brilen@samca.com  
**brilen.com**

**2024, BRILEN.**

The data contained in this manual are for general information purposes only. While they reflect the state of knowledge at the time of issue, BRILEN does not give any guarantee in respect there of and accepts no liability for deviations exhibited by their products.

# MEDIUM SHRINKAGE



## NLS - MEDIUM SHRINKAGE

Type	Titer/Filaments	Version	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA (%)
NLS	1100/192	HT00-HT10-HT20	78	13,0	6,0	<b>4,7</b>
	1440/192	HT00-HT20	77	13,0	6,0	<b>4,7</b>
	1670/192	HT00-HT20	77	13,0	6,0	<b>4,7</b>
	2200/384	HT00-HT10-HT20	76	13,0	6,0	<b>4,7</b>
	3300/384, 3300/576	HT00-HT10-HT20	76	13,0	6,0	<b>4,7</b>
	4400/576, 4400/768	HT00-HT20	76	13,0	6,0	<b>4,7</b>

## NLR - LOWER SHRINKAGE

Type	Titer/Filaments	Version	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA (%)
NLR	1100/192	HT20	77	19,0	9,0	<b>2,5</b>
	2200/384	HT20	77	19,0	9,0	<b>2,5</b>
	3300/384	HT20	77	19,0	9,0	<b>2,5</b>
	4400/768	HT20	77	19,0	9,0	<b>2,5</b>

## NLI - HIGHER TENACITY LOW SHRINKAGE

Type	Titer/Filaments	Version	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA (%)
NLI	1100/192	HT15	<b>90</b>	13,0	5,6	<b>5,1</b>

\*SHA analysed with LENZING (180°, 2 min and pretension: 0,5 cN/tex)

### FOOD CONTACT VERSION IS AVAILABLE

All our titer portfolio could accomplish FDA 21 CFR 177,2800 (textile and fibers) and Plastics Regulation (Framework Regulation No 1935/2004 and Regulation No 10/2011).

Any special request on properties, spool format or certification could be available under request. Please, contact our commercial team.